



# RAVAR SHIMI

Global Petrochemical Trading

Ravarshimi Co. LTD

## Product Technical Data sheet

### Penetration Grade Bitumen 85/100

Property	Unit	Typical Data	Test Methods
Density 25°C	-	1.01-1.05	ASTM D-7
Penetration 25°C	0.1MM	85-100	ASTM D-5
Softening point	°C	45-52	ASTM D-36
Ductility at 25°C cm	CM	100	ASTM D-113
Flash point	°C	250	ASTM D-92
Solubility disulfide	% wt	Min 99	ASTM D-4
Spot Test	-	Negative	AASHTO T 102
Loss on heating	% wt	0.2	ASTM D-6
Drop in Penetration after Heating	%	20	ASTM D-6-D-5

**For future information, please contact:**

**Ravarshimi co. LTD**

Iran, Tehran

**Website:** [www.ravarshimi.com](http://www.ravarshimi.com)

**Mail :** [info@ravarshimi.com](mailto:info@ravarshimi.com)

**Tel:** +9821 – 88510010 , 88766070