



# RAVAR SHIMI

Global Petrochemical Trading

Ravarshimi Co. LTD

## Product Technical Data sheet

Cutback

### Medium Curing Cutback Bitumen

Property	Typical Data		Test Methods
	Min	Max	
Kinematic viscosity at 60°C, mm <sup>2</sup> /s	250	500	ASTM D-2170
Flash point (Cleveland open cup), °C	66[150]	—	ASTM D-92
Distillation test: Distillate, volume percent of total distillate to 360°C:			ASTM D-402
to 225°C	—	20	
to 260°C	5	55	
to 316°C	60	90	
Residue from distillation to 360°C, percent volume by difference	67	—	
Tests on residue from distillation:			
Viscosity at 60°C, Pa	30	120	
Ductility at 25°C, cm	100	—	ASTM D-113
Solubility in trichloroethylene, %	99.09%	—	ASTM D-4
Water, %	—	0.2	ASTM D-95

**For future information, please contact:**

**Ravarshimi co. LTD**

Iran, Tehran

**Website:** [www.ravarshimi.com](http://www.ravarshimi.com)

**Mail :** [info@ravarshimi.com](mailto:info@ravarshimi.com)

**Tel:** +9821 – 88510010 , 88766070